

Provided By:



ESTIMATING CONCRETE MASONRY MATERIALS

INTRODUCTION

Estimating the quantity or volume of materials used in a typical masonry project can range from the relatively simple task associated with an unreinforced single wythe garden wall, to the comparatively difficult undertaking of a partially grouted multiwythe wall coliseum constructed of varying unit sizes, shapes, and configurations.

Large projects, due to their complexity in layout and detailing, often require detailed computer estimating programs or an intimate knowledge of the project to achieve a reasonable estimate of the materials required for construction. However, for smaller projects, or as a general means of obtaining ballpark estimates, the rule of thumb methods described in this TEK provide a practical means of determining the quantity of materials required for a specific masonry construction project.

It should be stressed that the information for estimating materials quantities in this section should be used with caution and checked against rational judgment. Design issues such as non-modular layouts or numerous returns and corners can significantly increase the number of units and the volume of mortar or grout required. Often, material estimating is best left to an experienced professional who has developed a second hand disposition for estimating masonry material requirements.

ESTIMATING CONCRETE MASONRY UNITS

Probably the most straightforward material to estimate for most masonry construction projects is the units themselves. The most direct means of determining the number of concrete masonry units needed for any project is to simply determine the total square footage of each wall and divide by the surface area provided by a single unit specified for the project.

For conventional units having nominal heights of 8 in. (203 mm) and nominal lengths of 16 in. (406 mm), the exposed surface area of a single unit in the wall is 8/9 ft² (0.083 m²). Including a 5 percent allowance for waste and breakage, this translates to 119 units per 100 ft² (9.29 m²) of wall area. (See Table 1 for these and other values.) Because this method of determining the necessary number of concrete masonry units for a given

project is independent of the unit width, it can be applied to estimating the number of units required regardless of their width.

When using this estimating method, the area of windows, doors and other wall openings needs to be subtracted from the total wall area to yield the net masonry surface. Similarly, if varying unit configurations, such as pilaster units, corner units or bond beam units are to be incorporated into the project, the number of units used in these applications need to be calculated separately and subtracted from the total number of units required.

ESTIMATING MORTAR MATERIALS

Next to grout, mortar is probably the most commonly misestimated masonry construction material. Variables such as site batching versus pre-bagged mortar, mortar proportions, construction conditions, unit tolerances and work stoppages, combined with numerous other variables can lead to large deviations in the quantity of mortar required for comparable jobs.

As such, masons have developed general rules of thumb for estimating the quantity of mortar required to lay concrete masonry units. These general guidelines are as follows for various mortar types. Note that the following estimates assume the concrete masonry units are laid with face shell mortar

Table 1—Approximate Number of Concrete Masonry Units Required for Single Wythe Construction^a

Unit type	Unit face size, in. (mm)	Number of units per 100 ft ² (100 m ²) of wall area
conventional	8 x 16 (203 x 406)	8 x 16 (203 x 406)
half-high	4 x 16 (102 x 406)	4 x 16 (102 x 406)
half-length	8 x 8 (203 x 203)	8 x 8 (203 x 203)
brick	2 2/3 x 8 (68 x 203)	22/3 x 8 (68 x 203)

^a based on net area of masonry wall, includes about 5% waste

Table 2—Mortar Estimation for Single Wythe Concrete Masonry Walls ^a

Mortar type & batch proportions	Approximate number of units that can be laid using one batch of mortar	
	Conventional CMU:	Brick-sized CMU:
Masonry cement: 8-70 lb (31.8 kg) bags masonry cement, 1 ton (907 kg) sand ^b	240	1,000
Preblended mortar: 1-80 lb (36.3 kg) bag 1-3,000 lb (1,361 kg) bag	16 420	50 1,550
Site-mixed mortar ^c :		
Portland cement-lime:		
Type M 1 ft ³ portland cement, ¼ ft ³ hydrated lime, 3¾ ft ³ sand	38	187
Type S 1 ft ³ portland cement, ½ ft ³ hydrated lime, 4½ ft ³ sand	46	225
Type N 1 ft ³ portland cement, 1 ft ³ hydrated lime, 6 ft ³ sand	62	300
Type O 1 ft ³ portland cement, 2 ft ³ hydrated lime, 9 ft ³ sand	93	450
Mortar cement:		
Type M 1 ft ³ portland cement, 1 ft ³ Type N mortar cement, 6 ft ³ sand, or 1 ft ³ Type M mortar cement, 3 ft ³ sand	62 31	300 150
Type S ½ ft ³ portland cement, 1 ft ³ Type N mortar cement, 4½ ft ³ sand, or 1 ft ³ Type S mortar cement, 3 ft ³ sand	46 31	225 150
Type N or O 1 ft ³ Type N mortar cement, 3 ft ³ sand	31	150
Masonry cement:		
Type M 1 ft ³ portland cement, 1 ft ³ Type N masonry cement, 6 ft ³ sand, or 1 ft ³ Type M masonry cement, 3 ft ³ sand	62 31	300 150
Type S ½ ft ³ portland cement, 1 ft ³ Type N masonry cement, 4½ ft ³ sand, or 1 ft ³ Type S masonry cement, 3 ft ³ sand	46 31	225 150
Type N or O 1 ft ³ Type N masonry cement, 3 ft ³ sand	31	150

^a Number of units can vary from those listed in the table, based on factors such as the skill level of the mason, non-modular layouts, numerous returns and corners, etc. Values include nominal amounts for waste. Assumes face shell mortar bedding for conventional concrete masonry units and full bedding for brick-sized concrete masonry units. 1 ft³ = 0.0283 m³.

^b 1 ton (907 kg) damp loose sand = 25 ft³ (0.71 m³)

^c For conversion purposes, the following can be used:

Portland cement: typical bag volume = 1 ft³ (0.028 m³); typical bag weight 94 lb (42.6 kg); typical density 94 lb/ft³ (1,506 kg/m³)

Hydrated mason's lime: typical bag volume = 11/4 ft³ (0.035 m³); typical bag weight 50 lb (22.7 kg); typical density 40 lb/ft³ (641 kg/m³)

Sand: 1 ft³ is equivalent to about 7 shovelfuls; typical density of damp loose sand 80 lb/ft³ (1,281 kg/m³)

Masonry and mortar cement bag weights vary, although commonly: Type N masonry cements and mortar cements are packaged in 70 lb (31.8 kg) bags; Type S masonry cements and mortar cements are packaged in 75 lb (34.0 kg) bags; Type M masonry cements and mortar cements are packaged in 80 lb (36.3 kg) bags.

bedding; hence, the estimates are independent of the concrete masonry unit width.

Masonry cement mortar

Masonry cement is typically available in bag weights of 70, 75 or 80 lb (31.8, 34.0 and 36.3 kg), although other weights may be available as well. One 70 lb (31.8 kg) bag of masonry cement will generally lay approximately 30 hollow units if face shell bedding is used. For common batching proportions, 1 ton (2,000 lb, 907 kg) of masonry sand is required for every 8 bags of masonry cement. If more than 3 tons (2,721 kg) of sand is used, add 1/2 ton (454 kg) to account for waste. For smaller sand amounts, simply round up to account for waste. This equates to about 240 concrete masonry units per ton of sand.

Preblended mortar

Preblended mortar mixes may contain portland cement and lime, masonry cement or mortar cement, and will always include dried masonry sand. Packaged dry, the mortars typically are available in 60 to 80 lb (27.2 to 36.3 kg) bags or in bulk volumes of 2,000 and 3,000 lb (907 and 1,361 kg).

Portland cement lime mortar

One 94 lb (42.6 kg) bag of portland cement, mixed in proportion with sand and lime to yield a lean Type S or rich Type N mortar, will lay approximately 62 hollow units if face shell bedding is used. This assumes a proportion of one 94 lb (42.6 kg) bag of portland cement to approximately one-half of a 50 lb (22.7 kg) bag hydrated lime to 4 1/4 ft³ (0.12 m³) of sand. For ease of

measuring in the field, sand volumes are often correlated to an equivalent number of shovels using a cubic foot (0.03 m³) box, as shown in Figure 1.

ESTIMATING GROUT

The quantity of grout required on a specific job can vary greatly depending upon the specific circumstances of the project. The properties and configuration of the units used in construction can have a huge impact alone. For example, units of low density concrete tend to absorb more water from the mix than comparable units of higher density. Further, the



Figure 1—Measuring Mortar Sand Volume

Table 3—Grout Volume Estimation for Hollow Single Wythe Concrete Masonry Walls

Volume of grout, ft³ per 100 ft² of wall (m³ per 100 m²)^a

Grout spacing, in. (mm)	Wall width:				
	6 in. (152 mm)	8 in. (203 mm)	10 in. (254 mm)	12 in. (305 mm)	14 in. (356 mm)
8 (203)	25.6(7.8)	36.1(11.0)	47.0(14.3)	58.9(18.0)	74.5(22.7)
16 (406)	12.8(3.9)	18.1(5.5)	23.5(7.2)	29.5(9.0)	37.3(11.4)
24 (610)	8.6(2.6)	12.1(3.7)	15.7(4.8)	19.7(6.0)	24.8(7.6)
32 (813)	6.4(2.0)	9.1(2.8)	11.8(3.6)	14.8(4.5)	18.6(5.7)
40 (1,016)	5.2(1.6)	7.3(2.2)	9.4(2.9)	11.8(3.6)	14.9(4.5)
48 (1,219)	4.3(1.3)	6.1(1.9)	7.9(2.4)	9.9(3.0)	12.4(3.8)
56 (1,422)	3.7(1.1)	5.2(1.6)	6.8(2.1)	8.5(2.6)	10.6(3.2)
64 (1,626)	3.2(1.0)	4.6(1.4)	5.9(1.8)	7.4(2.3)	9.3(2.8)
72 (1,829)	2.9(0.9)	4.1(1.2)	5.3(1.6)	6.6(2.0)	8.3(2.5)
80 (2,032)	2.6(0.8)	3.7(1.1)	4.7(1.4)	5.9(1.8)	7.5(2.3)
88 (2,235)	2.4(0.7)	3.3(1.0)	4.3(1.3)	5.4(1.6)	6.8(2.1)
96 (2,438)	2.2(0.7)	3.1(0.9)	4(1.2)	5(1.5)	6.2(1.9)
104 (2,642)	2(0.6)	2.8(0.9)	3.7(1.1)	4.6(1.4)	5.7(1.7)
112 (2,845)	1.9(0.6)	2.6(0.8)	3.4(1.0)	4.3(1.3)	5.3(1.6)
120 (3,048)	1.8(0.5)	2.5(0.8)	3.2(1.0)	4(1.2)	4.9(1.5)

^a Assumes two-core hollow concrete masonry units and 3% waste.

method of delivering grout to a masonry wall (pumping versus bucketing) can introduce different amounts of waste. Although the absolute volume of grout waste seen on a large project may be larger than a comparable small project, smaller projects may experience a larger percentage of grout waste.

Table 3 provides guidance for the required volume of grout necessary to fill the vertical cells of walls of varying thickness. Additional grout may be necessary for horizontally grouting discrete courses of masonry. Note that walls constructed of 4-in. (102-mm) masonry units are not included in Table 3. Due to the small cell size and difficulty in adequately placing and consolidating the grout, it is not recommended to grout conventional 4-in. (102-mm) units.

Tables 4 and 5 contain estimated yields for bagged preblended grouts for vertical and horizontal grouting, respectively.

Table 4—Grout Estimation for Hollow Single Wythe Concrete Masonry Walls, Vertical Grouting with Preblended Grout^a

CMU size, in. (mm)	Yield, number of cores	
	80 lb (36.3 kg) bag	3,000 lb (1,361 kg) bag
6 (152)	3.6	150
8 (203)	2.7	110
10 (254)	2.2	95
12 (305)	1.8	80

^a 80 lb (36.3 kg) bag yields approximately 0.66 ft³ (0.019 m³); 3,000 lb (1,361 kg) bag yields approximately 25 ft³ (0.71 m³)

Table 5—Grout Estimation for Hollow Single Wythe Concrete Masonry Walls, Horizontal (Bond Beam) Grouting with Preblended Grout^a

CMU size, in. (mm)	Yield, linear ft (m)	
	80 lb (36.3 kg) bag	3,000 lb (1,361 kg) bag
6 (152)	2.7(0.823)	100(30.48)
8 (203)	2.0(0.609)	80(24.38)
12 (305)	1.6(0.488)	60(18.29)

^a 80 lb (36.3 kg) bag yields approximately 0.66 ft³ (0.019 m³); 3,000 lb (1,361 kg) bag yields approximately 25 ft³ (0.71 m³)

REFERENCES

1. *Kreh, D. Building With Masonry, Brick, Block and Concrete.* The Taunton Press, 1998.
2. *Annotated Design and Construction Details for Concrete Masonry,* CMU-MAN-001-03, Concrete Masonry & Hardscapes Association, 2003..

ABOUT CMHA

The Concrete Masonry & Hardscapes Association (CMHA) represents a unification of the Interlocking Concrete Pavement Institute (ICPI) and National Concrete Masonry Association (NCMA). CMHA is a trade association representing US and Canadian producers and suppliers in the concrete masonry and hardscape industry, as well as contractors of interlocking concrete pavement and segmental retaining walls. CMHA is the authority for segmental concrete products and systems, which are the best value and preferred choice for resilient pavement, structures, and living spaces. CMHA is dedicated to the advancement of these building systems through research, promotion, education, and the development of manufacturing guides, design codes and resources, testing standards, and construction practices.

Disclaimer:

The content of this CMHA Tech Note is intended for use only as a guideline and is made available “as is.” It is not intended for use or reliance upon as an industry standard, certification or as a specification. CMHA and those companies disseminating the technical information contained in the Tech Note make no promises, representations or warranties of any kind, expressed or implied, as to the accuracy or completeness of content contained in the Tech Note and disclaim any liability for damages or injuries resulting from the use or reliance upon the content of Tech Note. Professional assistance should be sought with respect to the design, specifications, and construction of each project.